

Piolas de Algodón

Piolas de Algodón

NO.	Resistencia		Rendimiento	
	kgs	lbs	mtrs/kg	pies/lb
6	7.7	17.0	2,439	3,629
9	11.6	25.6	1,408	2,095
12	15.5	34.2	1,124	1,672
15	19.4	42.8	877	1,305
18	23.3	51.4	746	1,110
21	27.2	60.0	613	912
24	31.1	68.6	513	763
27	35.0	77.2	474	705
30	38.9	85.8	417	620
36	46.7	103.0	336	500
42	54.5	120.2	329	489
48	62.3	137.3	267	397
54	70.1	154.5	242	360
60	70.6	155.6	219	326
72	93.5	206.1	182	271
84	109.0	240.3	151	225
96	124.6	274.7	131	195
120	155.8	343.5	102	152

Cifras aproximadas

Piolas de Nylon

Piolas de Nylon

NO.	Denier	Resistencia		Rendimiento	
	total	kgs	lbs	mtrs/kg	pies/lb
0	630	4.1	9.0	13,142	19,553
1	1260	8.2	18.1	6,571	9,776
3	1890	12.3	27.1	4,380	6,517
5	2520	17.6	38.8	3,298	4,907
6	3150	22.0	48.5	2,628	3,910
9	5040	35.3	77.8	1,642	2,443
12	6300	44.1	97.2	1,314	1,955
15	7560	52.9	116.6	1,015	1,510
18	10080	75.6	166.7	803	1,195
21	11340	79.4	175.0	714	1,062
24	12600	88.2	194.4	602	896
27	13860	97.0	213.8	584	869
30	15120	105.8	233.2	535	796
36	18900	132.3	291.7	428	637
42	22680	158.8	350.1	357	531
48	25200	179.2	395.1	321	478
54	27720	194.0	427.7	292	434
60	30240	211.7	466.7	261	388
72	37800	264.6	583.3	209	311
84	45360	317.5	700.0	174	259
96	50400	352.8	777.8	157	234
120	60480	423.4	933.4	103	153

Cifras aproximadas

Piola de Polipropileno

Piola de Polipropileno

No.	Presentación		Colores	
18	100 mtrs	200 mtrs	Blanco	Amarillo